

TECHNICAL FEATURES			
Collecion	Interiors	Brand	Marazzi
Size (cm)	20x50	Thickness (mm)	8,5

Compliant with standard EN 14411:2012 annex L group BIII - GL

Compliant with standard ISO 13006:2012 annex L group BIII - GL

Technical Features	Testing Method	Meas. unit	Average Typical Values	Established limits
<b>DIMENSIONAL PROPERTIES AND SURFACE QUALITY</b>				
Dimensions				Nominal Length of edge N (cm) 7≤N<15 Nominal Length of edge N (cm) N≥15
Length and width (*)	ISO 10545-2	(mm) (%)	Complies with the standards	±2% (max 5mm) ±2% (max 5mm)
Length and width (**)			Complies with the standards	±0,75 mm ±0,5 %
Thickness			Complies with the standards	±0,5 mm ±10 %
Straightness of sides			Complies with the standards	±0,5 mm ±0,3 %
Rectangularity			Complies with the standards	±0,75 mm ±0,5 %
Surface Flatness c.c - e.c.			Complies with the standards	+0,75 mm -0,50 mm +0,5 % -0,3 %
Surface Flatness w.			Complies with the standards	± 0,75 mm ±0,5 %
Surface Quality			(%)	Complies with the standards
<b>PHISICAL PROPERTIES</b>				
Water absorption	ISO 10545-3	(%)	> 10	Eb>10 (Individual minimun value 9%)
Modulus of rupture	ISO 10545-4	(N/mm2)	>= 12	R ≥15 (Thickness < 7,5 mm) R ≥12 (Thickness ≥7,5 mm)
Breaking strenght	ISO 10545-4	(N)	>= 600	≥600 (Thickness ≥7,5 mm) ≥200 (Thickness < 7,5 mm)
Linear thermal expansion coefficient	ISO 10545-8	(x(10)-6/°C)	<=9	Declared value (EN 14411:2012) Testing Method available (ISO 13006:2012)
Thermal shock resistance	ISO 10545-9		Complies with the standards	Declared value (EN 14411:2012) **** Test Method available (secondo ISO 13006:2012)
Crazing Resistance	ISO 10545-11		Complies with the standards	Pass according to EN ISO 10545-1 (EN 14411:2012) Required (ISO 13006:2012)
Recation to fire	-	-	Wall Class A1	Class A1 or Class A1 FL (EN 14411:2012)
Colour resistance to light exposure	DIN 51094		Complies with the standards	No sample must show noticeable colour modifications.

**TECHNICAL FEATURES**

Collecion	Interiors	Brand	Marazzi
Size (cm)	20x50	Thickness (mm)	8,5

**CHEMICAL PROPERTIES**

Resistance to chemicals for household use and swimming pool salts	ISO 10545-13		GA	GB Minimum (EN 14411:2012) GB Minimum (ISO 13006:2012)
Resistance to low concentrations of acids and alkalis	ISO 10545-13		GLA-GLB	Declared value (EN 14411:2012) Testing Method available (ISO 13006:2012)
Resistance to high concentrations of acids and alkalis	ISO 10545-13		GHA-GHB	Declared value (EN 14411:2012) Testing Method available (ISO 13006:2012)
Stain resistance	ISO 10545-14		Class 5	Minimum class 3 (EN 14411:2012) Minimum class 3 (ISO 13006:2012)

\* The work size shall be chose, for non-modular tiles, so that the difference between the work size and the nominal size is:

\*\* The deviation, in percent, of the average size for each tile (2 or 4 sides) from the work size..

\*\*\*\* See Table 2 for uses where it is applicable

c.c. Centre curvature, related to diagonal calculated from the work sizes

e.c. Edge curvature, related to the corresponding work sizes.

w. Warpage, related to diagonal calculated from the work sizes.

**TECHNICAL FEATURES**

Collecion	Interiors	Brand	Marazzi
Size (cm)	20x50	Thickness (mm)	8,5