











NX.PROSTONE

FORMATO/ <i>FORMAT</i>	60X60
ESPESOR/ <i>THICKNESS (mm)</i>	9,5
PRODUCTO/ <i>PRODUCT</i>	PORCELANICO/ PORCELAIN
TIPO/ <i>KIND</i>	NO ESMALTADO/ <i>UNGLAZED</i>
GRUPO/ <i>GROUP</i>	Bla - UGL

NORMA APLICABLE EN 14411 ANEXO G
APPLICABLE STANDARD ISO 13006 ANNEX G

ENSAYOS/ <i>TESTS</i>		RESULTADOS/ <i>RESULTS</i>	
	UNE-EN ISO 10545-2 DIMENSIONES Y ASPECTO SUPERFICIAL <i>UNE-EN ISO 10545-2 DIMENSIONS AND SURFACE QUALITY</i>	DIMENSIONES <i>DIMENSIONS</i>	CUMPLE CON LA NORMA <i>COMPLIES WITH THE STANDARD</i>
	UNE-EN ISO 10545-3 ABSORCIÓN DE AGUA <i>UNE-EN ISO 10545-3 WATER ABSORPTION</i>	VALOR MEDIO (%) <i>AVERAGE VALUE (%)</i>	≤ 0,5 %
	UNE-EN ISO 10545-4 RESISTENCIA A LA FLEXIÓN <i>UNE-EN ISO 10545-4 MODULUS OF RUPTURE</i>	FUERZA DE ROTURA <i>BREAKING STRENGTH (N)</i> RESISTENCIA A LA FLEXIÓN <i>MODULUS OF RUPTURE (N/mm²)</i>	1600 - 2400 N 35 - 45 N/mm ²
	UNE-EN ISO 10545-6 RESISTENCIA A LA ABRASIÓN PROFUNDA <i>UNE-EN ISO 10545-6 RESISTANCE TO DEEP ABRASION</i>	ABRASIÓN PROFUNDA <i>DEEP ABRASION (mm³)</i>	< 130 mm ²
	UNE-EN ISO 10545-9 RESISTENCIA AL CHOQUE TÉRMICO <i>UNE-EN ISO 10545-9 THERMAL RESISTANCE</i>	RESULTADO <i>RESULT</i>	RESISTE <i>RESISTS</i>
	UNE-EN ISO 10545-12 RESISTENCIA A LA HELADA <i>UNE-EN ISO 10545-12 FROST RESISTANCE</i>	RESULTADO <i>RESULT</i>	RESISTE <i>RESISTS</i>
	UNE-EN ISO 10545-13 RESISTENCIA QUÍMICA <i>UNE-EN ISO 10545-13 CHEMICAL RESISTANCE</i>	CLORURO AMÓNICO <i>AMMONIUM CHLORIDE 100 g/l</i> HIPOCLORITO SÓDICO <i>SODIUM HYPOCHLORITE 20 mg/l</i> ÁCIDO CLORHÍDRICO <i>HYDROCHLORIC ACID 3%</i> ÁCIDO CÍTRICO <i>CITRIC ACID 100 g/l</i> HIDRÓXIDO POTÁSICO <i>POTASSIUM HYDROXYDE 30 g/l</i>	A A CUMPLE CON LA NORMA <i>COMPLIES WITH THE STANDARD</i>
	UNE-EN ISO 10545-14 RESISTENCIA A LAS MANCHAS <i>UNE-EN ISO 10545-14 STAIN RESISTANCE</i>	ÓXIDO VERDE EN ACEITE LIGERO <i>GREEN AGENT IN LIGHT OIL</i> SOLUCIÓN ALCOHÓLICA DE YODO <i>IODINE SOLUTION IN ALCOHOL</i> ACEITE DE OLIVA <i>OLIVE OIL</i>	5 5 5
	DIN 51130 ÁNGULO CRÍTICO DE DESLIZAMIENTO (RAMPA) <i>DIN 51130 CRITICAL ANGLE OF SLIP (INCLINED PLATFORM)</i>	RESULTADO <i>RESULT</i>	R10
	DIN 51097:1992 ÁNGULO CRÍTICO DE DESLIZAMIENTO. ZONAS HÚMEDAS DE ANDAR DESCALZO <i>DIN 51097:1992 CRITICAL ANGLE OF SLIP. WET-LOADED BAREFOOT AREAS</i>	CLASE <i>CLASS</i>	B

OBSERVACIONES:

V⁰B⁰ LABORATORIO:

